

PARTIALLY ORIENTED POLYESTER YARN

Patent Number: JP2001254226
Publication date: 2001-09-21
Inventor(s): FUJIMOTO KATSUHIRO;; KATO JINICHIRO
Applicant(s): ASAHI KASEI CORP
Requested Patent: ☐ JP2001254226
Application Number: JP20000062882 20000308
Priority Number(s):
IPC Classification: D01F6/62; D02G1/02
EC Classification:
Equivalents:

Abstract

PROBLEM TO BE SOLVED: To provide a PTT-POY(poly (trimethylene terephthalate)-partially oriented yarn) which can Industrially be produced by controlling the generation of tight winding and bulge and can industrially stably give a high grade false- twisted yarn free from dyeing irregularity and so on without fuzzing and breaking the yarn.

SOLUTION: This PTT-POY has a high elongation and a low relaxation shrinkage and has no irregularity of yarn diameter and structure. The method for producing the PTT-POY is characterized by employing a special spinning method which comprises winding up the yarn at a specific contact pressure and at a specified leasing angle, thereby lowering the temperature of the wound yarn at the winding time and winding up the yarn at a low winding tension without damaging the wound yarn.

Data supplied from the esp@cenet database - I2